



# ACM 产品规格表一

	铜母线：标准载流量			铜铝复合母线					
				与铜母线相同载流量			相当于铜母线 86%载流量		
	规格(mm)	kg/m	kg/根	规格(mm)	kg/m	kg/根	规格(mm)	kg/m	kg/根
	1#生产线								
1	30 系列								
1.1	30*3	0.783	4.697	30*3.5	0.403	2.421	30*3	0.347	2.081
1.2	30*4	1.036	6.217	30*4.6	0.534	3.202	30*4	0.459	2.754
1.3	30*5	1.286	7.714	30*5.8	0.663	3.977	30*5	0.570	3.417
1.4	30*6	1.531	9.188	30*7.0	0.788	4.730	30*6	0.678	4.070
2	40 系列								
2.1	40*3	1.050	6.298	40*3.5	0.541	3.244	40*3	0.465	2.790
2.2	40*4	1.392	8.351	40*4.6	0.716	4.298	40*4	0.616	3.699
2.3	40*5	1.730	10.381	40*5.8	0.891	5.344	40*5	0.766	4.599
2.4	40*6	2.065	12.389	40*7.0	1.064	6.384	40*6	0.915	5.488
3	50 系列								
3.1	50*3	1.316	7.898	50*3.5	0.678	4.067	50*3	0.583	3.498
3.2	50*4	1.747	10.485	50*4.6	0.900	5.400	50*4	0.774	4.644
3.3	50*5	2.175	13.048	50*5.8	1.120	6.719	50*5	0.963	5.780
3.4	50*6	2.598	15.589	50*7.0	1.338	8.030	50*6	1.151	6.906
	2#生产线								
4	60 系列								
4.1	60*4	2.103	12.618	60*4.6	1.084	6.502	60*4	0.932	5.589
4.2	60*5	2.619	15.715	60*5.8	1.349	8.093	60*5	1.160	6.961
4.3	60*6	3.132	18.790	60*7.0	1.613	9.677	60*6	1.387	8.323
4.4	60*8	4.145	24.869	60*9.3	2.135	12.809	60*8	1.836	11.016
5	80 系列								
5.1	80*4	2.814	16.885	80*4.6	1.450	8.700	80*4	1.247	7.480
5.2	80*5	3.508	21.049	80*5.8	1.807	10.842	80*5	1.554	9.324
5.3	80*6	4.198	25.190	80*7.0	2.163	12.977	80*6	1.860	11.159
5.4	80*8	5.567	33.404	80*9.3	2.867	17.205	80*8	2.466	14.797
5.5	80*10	6.921	41.525	80*11.6	3.565	21.390	80*10	3.066	18.394
6	100 系列								
6.1	100*4	3.525	21.153	100*4.6	1.816	10.898	100*4	1.562	9.370
6.2	100*5	4.397	26.383	100*5.8	2.265	13.591	100*5	1.948	11.687
6.3	100*6	5.265	31.591	100*7.0	2.712	16.270	100*6	2.332	13.994
6.4	100*8	6.990	41.938	100*9.3	3.600	21.600	100*8	3.096	18.577
6.5	100*10	8.699	52.193	100*11.6	4.480	26.881	100*10	3.853	23.120
6.6	100*12	10.393	62.357	100*13.9	5.353	32.121	100*12	4.604	27.622

说明：1、铜铝复合母线设计铜层体积比 20%、设计密度 3.938g/cm<sup>3</sup>；

2、铜铝复合母线设计全圆边截面，设计定尺长度 6m/根。



# ACM 产品规格表二

	铜铝复合母线								
	铜母线：标准载流量			与铜母线相同载流量			相当于铜母线 86%载流量		
	规格(mm)	kg/m	kg/根	规格(mm)	kg/m	kg/根	规格(mm)	kg/m	kg/根
	3#生产线								
7	120 系列								
7.1	120*6	6.332	37.992	120*7.0	3.262	19.570	120*6	2.805	16.829
7.2	120*8	8.412	50.472	120*9.3	4.333	25.995	120*8	3.726	22.358
7.3	120*10	10.477	62.861	120*11.6	5.397	32.379	120*10	4.641	27.846
7.4	120*12	12.526	75.158	120*13.9	6.452	38.714	120*12	5.549	33.293
8	140 系列								
8.1	140*6	7.399	44.393	140*7.0	3.810	22.863	140*6	3.277	19.665
8.2	140*8	9.834	59.007	140*9.3	5.065	30.391	140*8	4.356	26.18
8.3	140*10	12.255	73.529	140*11.6	6.309	37.856	140*10	5.426	32.571
8.4	140*12	14.660	87.960	140*13.9	7.551	45.307	140*12	6.494	38.964
9	160 系列								
9.1	160*6	8.466	50.793	160*7.0	4.360	26.163	160*6	3.750	22.500
9.2	160*8	11.257	67.541	160*9.3	5.798	34.786	160*8	4.986	29.919
9.3	160*10	14.033	84.197	160*11.6	7.228	43.367	160*10	6.216	37.297
9.4	160*12	16.794	100.761	160*13.9	8.650	51.900	160*12	7.439	44.634
	4#生产线								
10	180 系列								
10.1	180*6	9.532	57.194	180*7.0	4.910	29.463	180*6	4.223	25.335
10.2	180*8	12.679	76.076	180*9.3	6.531	39.188	180*8	5.617	33.699
10.3	180*10	15.811	94.865	180*11.6	8.144	48.865	180*10	7.004	42.022
10.4	180*12	18.927	113.563	180*13.9	9.749	58.493	180*12	8.384	50.305
11	200 系列								
11.1	200*6	10.599	63.595	200*7.0	5.459	32.756	200*6	4.695	28.171
11.2	200*8	14.102	84.610	200*9.3	7.264	43.584	200*8	6.247	37.480
11.3	200*10	17.589	105.533	200*11.6	9.059	54.356	200*10	7.791	46.748
11.4	200*12	21.061	126.365	200*13.9	10.848	65.086	200*12	9.329	55.976

说明：1、铜铝复合母线设计铜层体积比 20%、设计密度 3.938g/cm<sup>3</sup>；

2、铜铝复合母线设计全圆边截面，设计定尺长度 6m/根。